



HOT SPLICE FABRIC PRIMER



Photo shows 1 quart.

Hot Splice Fabric Primer is a one part coating for RFL treated fabric that enhances adhesions in hot vulcanized belt splicing. It is designed for use as a reactive bonding agent between bare fabric surfaces and uncured splice materials.

FEATURES:

- Can be mixed directly into the HC1 splice cement as an adhesion additive (mix no more than 10% by volume, use within 3 hours)
- Has excellent brushable consistency for ease of application
- Good penetration into the RFL treated fabric
- For Natural Rubber (NR), Polyisoprene (IR), Styrene-Butadiene (SBR), Polybutadiene (BR), Polychloroprene i.e. - Neoprene (CR) rubber belt splices

PROPERTIES	
Colour	Black
Base	Mixture of polymers
Solids (wt.)	20 - 25%
Solvent	Xylene
Calculated Coverage	144 sf / gal / mil
Flash Point	Closed Cup 77°F
Shelf Life	6 months at 70°F or 12 months at 50°F

PRODUCT CODE	Label Colour	Unit Volume		Product Weight	
		Gal	litre	kg	lb
AA-HFP-Q	Green	Quart	.95	.9	1.98



Note: The above data is based on extensive testing and represents standard values. Shaw Almex Industries reserves the right to make changes without prior notice and refuses all claims arising from such changes. All items are subject to change without previous notice.

Updated: Dec. 2011